

*Creative Paradise Inc.*

## SLURRY DROP CENTER DISH

Use compatible glass throughout. Apply Zyp BN Spray to the GM232 Small Round Shelf Ring mold (and the texture mold if a textured bottom is desired).

Cut a 7.5" diameter of 6 mm Clear Glass. Clean the glass to remove any oils.

Using the Basic Slurry technique provided and apply a slurry design to the 7.5" circle of glass. Clean any slurry from the edges and from the underside of the clear glass and allow the slurry to dry. In most conditions, the slurry can be dry enough to fire within several hours.

Place the shelf ring either a piece of kiln shelf paper or onto a texture mold on a level kiln shelf and fire using the firing schedule found in Table 1.



Table 1

Segment	Rate	Temp	Hold
1	275	1150	20
2	50	1330	30
3	450	1420	10
4	9999	950	90
5	100	500	0

